



Technical Data Sheet

Quality Specification

Palm Twin

	Basis Weigth	Bursting Strength	Burst Index	SCT, CD	SCT, CD	CMT 30	CMT 30
Dimension	[g/m ²]	[kPa]	[kPa m ² /g]	[kN/m]	[kN/m]	[N]	[N]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895	ISO 7263	ISO 7263
Tolerance	± 3 %	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel	Average per Delivery	Minimum per Reel
	80	160	2.0	1.40	1.30	-	-
	85	170	2.0	1.50	1.40	-	-
	90	180	2.0	1.60	1.50	-	-
	100	200	2.0	1.70	1.60	-	-
	110	220	2.0	1.90	1.80	180	170
	125	250	2.0	2.10	2.00	200	190
	130	260	2.0	2.25	2.10	210	200
	150	300	2.0	2.55	2.40	230	220

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Issue date 1 June 2023