



Technical Data Sheet

Quality Specification

Palm Top 68 H

	Basis Weight	Bulk	Brightness	Breaking Length (MD)	Opacity	Roughness (TS/BS) Bendtsen	Gloss Hunter (75°)
Dimension	[g/m ²]	[cm ³ /g]	[%]	[m]	[%]	[ml/min]	[%]
Standard	ISO 536	ISO 534	ISO 2470	ISO 1924	ISO 2471	ISO 8791-2	ISO 8254-1
	45.0	1.2	68	5,500	94.0	40	22
	48.8	1.2	68	5,500	95.0	40	22
	52.0	1.2	68	5,500	96.0	40	22

Colour Specification:	Standard ISO 5631	L* (C/2°) 85.0 a* (C/2°) 0.0 b* (C/2°) 3.5
Preconditioning:	ISO 187, 23°C, 50% relative humidity	
Tolerance:	The tolerances are within the industrial standard range.	
Certificates:	ISO 9001, ISO 14001, ISO 45001, ISO 50001, FSC®, PEFC, Blue Angel (Note our licence numbers: FSC® C127275, FSC® C041166, PEFC/04-31-2442.)	
PrePress Guidelines:	ICC Paper Profile: PSO_INP_Paper_eci.icc Characterisation data: FOGRA48L.txt	
Raw Material:	100 % recycled	

Issue date 15 March 2023

www.palm.de